
Target Values: Ancora[®] C2S

English (mils, lbs/3msf)	nominal	10-144	12-167	14-188	16-203	18-220	20-240	22-265	24-286
Metric (µm, g/sq m)	nominal	254-234	305-272	356-306	406-330	457-358	508-391	559-431	610-465
Caliper	mils	10	12	14	16	18	20	22	24
Basis Weight	lbs/3msf	144	167	188	203	220	240	265	286
Brightness (Both Sides)	GE	90	90	90	90	90	90	90	90
Coated b* Color (Both Sides)	Spectro	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
Smoothness (Both Sides)	Sheffield	6	8	9	11	12	14	15	16
Parker Print (Both Sides)	microns	1.3	1.4	1.4	1.4	1.5	1.5	1.5	1.5
Plybond	lbs/in ²	56	52	48	48	48	48	48	48
Stiffness - MD	Taber g-cm	60	90	130	185	256	330	415	520
Stiffness - CD	Taber g-cm	30	47	72	100	130	175	230	275

Stiffness values represent end-of-machine testing.
These values may change.

Document Revision Date: July 2011
