

Target Values: Candesce® Blister

English (mils, lbs/3msf)	nominal	12-143	14-163	16-182	18-199	20-217	22-233	24-250	26-273
Metric (µm, g/sq m)	nominal	305-233	356-266	406-297	457-324	508-354	559-380	610-407	660-444
Caliper	mils	12	14	16	18	20	22	24	26
Basis Weight	lbs/3msf	143	163	182	199	217	233	250	273
Brightness	GE	88	88	88	88	88	88	88	88
Coated 'b' Color	Spectro	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Coated Smoothness	Sheffield	15	19	20	25	25	30	30	32
Parker Print	microns	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2
Plybond	lbs/in2	47.0	42.0	37.0	35.5	35.5	35.5	35.5	35.5
Stiffness - MD	Taber g-cm	90	125	160	215	265	310	415	495
Stiffness - CD	Taber g-cm	52	68	90	125	150	185	225	270

Stiffness values represent end-of-machine testing.
These values may change.

Document Revision Date: July 2011