

Target Values: Candesce® Foldover Blister

English (mils, lbs/3msf)	nominal	14-176	16-195	18-212	20-230	22-246	24-263	26-286
Metric (µm, g/sq m)	nominal	356-286	406-317	457-345	508-374	559-400	610-428	660-465
Caliper	mils	14	16	18	20	22	24	26
Basis Weight	lbs/3msf	176	195	212	230	246	263	286
Brightness	GE	88	88	88	88	88	88	88
Coated 'b' Color	Spectro	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Coated Smoothness	Sheffield	19	20	25	25	30	30	32
Parker Print	microns	1.2	1.2	1.2	1.2	1.2	1.2	1.2
Plybond	lbs/in ²	42.0	37.0	35.5	35.5	35.5	35.5	35.5
Stiffness - MD	Taber g-cm	125	160	215	265	310	415	495
Stiffness - CD	Taber g-cm	68	90	125	150	185	225	270

Stiffness values represent end-of-machine testing.
These values may change.

Document Revision Date: July 2011